



Palio LooseLay Technical Data



	Standard	Result
Size	EN ISO 24342	See separate table
Thickness	EN ISO 24346	4.5 mm
Wear layer	EN ISO 24340	0.55 mm
Surface treatment		PU coating
Guarantee	Light industrial Commercial Domestic	15 years* 15 years* Lifetime guarantee*
Bevelled edge		No
Mass	EN ISO 23997	7550 g/m ²
Standards	EN 649/EN ISO 10582	Pass
Classification	EN 685/EN ISO 10874 - Light industrial EN 685/EN ISO 10874 - Commercial EN 685/EN ISO 10874 - Domestic	42: Light industrial general 33: Commercial heavy 23: Domestic heavy
Reaction to fire	EN 13501-1	B _{fl} -s1
Staining resistance	EN 423	Class 0
Light fastness	EN ISO 105-B02	7
Abrasion resistance	EN 649 EN ISO 10582	Group T Type 1
Flexibility	EN ISO 24344	Pass
Dimensional stability	EN 434/ EN ISO 23999	≤ 0.10%
Acoustic impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL _w = 13 dB
Electrical behaviour body voltage	EN 1815	Pass
Indentation - residual	EN 433/EN ISO 24343-1	Pass ≤ 0.1mm
Castor chair continuous use	EN 425/ISO 4918	Pass
Thermal resistance	ISO 8302	0.0245 m ² K/W Suitable for underfloor heating. Max 27°C
**Slip resistance	BS 7976 DIN 51130 DIN 51097 EN 13893	See separate table R10 See separate table DS
Light reflectance value (LRV)	BS 8493:2008+A1:2010	See separate table
VOC emission	French VOC regulation (ISO 16000)	A+
Adhesive		Please refer to our installation instructions.
Recycling		Suitable

Product	Size (mm)	Slip Resistance			LRV
		BS 7976 (dry)	BS 7976 (wet)	DIN 51097	
LLP142	1050 X 250	61	33	B	26
LLP143	1050 X 250	61	33	B	20
LLP144	1050 X 250	61	33	B	34
LLP145	1050 X 250	61	33	B	27
LLP146	1050 X 250	61	33	B	27
LLP147	1050 X 250	61	33	B	38
LLP148	1050 X 250	61	33	B	21
LLP149	1050 X 250	61	33	B	46
LLP150	1050 X 250	61	33	B	25
LLP151	1050 X 250	61	33	B	9
LLT208	610 x 500	66	29	A	66
LLT209	610 x 500	66	29	A	44
LLT210	610 x 500	66	29	A	23
LLT211	610 x 500	66	29	A	10

*Subject to terms. Please see our website.

**Slip resistance is measured on ex-factory product. Slip resistance can be affected by surface contamination, use and how the product is maintained

For more information:

Call: 01386 820200 For ROI call: 01 6569887

Email: info@palioflooring.com

Visit: www.palioflooring.com

Manufactured to ISO9001

