



	Standard	Result	Product	Size (mm)	LRV
Size	EN ISO 24342	See separate table	PVP142	1219.2 x 177.8(48"x7")	26
Thickness	EN ISO 24346	2.0 mm	PVP143	1219.2 x 177.8(48"x7")	20
Wear layer	EN ISO 24340	0.3 mm	PVP144	1219.2 x 177.8(48"x7")	34
Surface treatment		PU coating	PVP145	1219.2 x 177.8(48"x7")	27
Guarantee	Light industrial	n/a	PVP146	1219.2 x 177.8(48"x7")	27
	Commercial	10 years*	PVP147	1219.2 x 177.8(48"x7")	38
	Residential	Lifetime guarantee*	PVP148	1219.2 x 177.8(48"x7")	21
Bevelled edge		No	PVP149	1219.2 x 177.8(48"x7")	46
Mass	EN ISO 23997	3360 g/m ²	PVP150	1219.2 x 177.8(48"x7")	25
Standards	EN 649/ EN ISO 10582	Pass	PVP151	1219.2 x 177.8(48"x7")	9
Classification	EN 685/EN ISO 10874- Light industrial	n/a	PVT1201	457.2 x 304.8(18"x12")	6
	EN 685/EN ISO 10874- Commercial	31: Commercial moderate	PVT1202	457.2 x 304.8(18"x12")	50
	EN 685/EN ISO 10874- Domestic	23: Domestic heavy	PVT1203	457.2 x 304.8(18"x12")	41
Reaction to fire	EN 13501-1	B _{f1} -s1	PVT1204	457.2 x 304.8(18"x12")	33
Staining resistance	EN ISO 26987/EN 423	Excellent			
Light fastness	EN ISO 105-B02	≥6			
Abrasion resistance	EN 649/ EN ISO 10582	Group T			
	EN ISO 10582	Type 1			
Flexibility	EN ISO 24344	Pass			
Dimensional stability	EN 434/ EN ISO 23999	Pass			
Acoustic Impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL _w = 1 dB			
Electrical behaviour body voltage	EN 1815	Pass			
Indentation - residual	EN 433/ EN ISO 24343-1	Pass ≤ 0.1mm			
Castor chair continuous use	EN 425/ISO 4918	Pass			
Thermal resistance	EN 12664	0.0107 m ² K/W			
		Suitable for underfloor heating. Max 27°C			
Slip resistance**	DIN 51130	R10			
	EN 13893	DS			
Light reflectance value (LRV)	BS 8493:2008+A1:2010	See separate table			
VOC emission	ISO 16000	Indoor Air Comfort Gold			
Adhesive	Karndean Universal	Yes			
	Acrylic	Yes			
	Epoxy	Yes			
	High Temperature	Yes			
	Pressure sensitive	Yes			
Recycling		Suitable			
Phthalate free		Yes			

*Subject to terms. Please see our website.

** Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors, including but not limited to; product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.

For more information:

Call: 01386 820110

For ROI call: 01 6569887

Email: info@palioflooring.com

Visit: www.palioflooring.com



EN 14041:2004 (DOP 2017/PGluedown/EN/01)
Notified body 0321
Floor Coverings: (Internal)
ISO 10874 Class 23/31
Manufactured to ISO 10582

